

Modena / Carina

polipiel / eco leather
by Coleccion Alexandra

vers. **01**

COLECCION
ALEXANDRA

Finest Spanish Handicraft

Modena


polipiel / eco leather
by Coleccion Alexandra



Q-1007



Q-1000




Q-1019




Q-1013




Q-1029




Q-1031



Q-1028




Q-1017




Q-1020




Q-1016




Q-1001




Q-1011




Q-1005




Q-1018




Q-1002




Q-1021



Q-1009



Q-1033




Q-1034



Q-1012



Q-1035




Q-1015



Q-1036




Q-1004



Q-1014



Q-1032



Q-1037

Carina

polipiel / eco leather
by Coleccion Alexandra



F-2880



F-2881



F-2882

Modena

polipiel / eco leather

Grupo de precio

Z

Composición

68% pvc - 2% poliuretano - 30% algodón

Ancho

± 140 cm / 55 in.

Peso

± 640 gr/m²

Espesor

± 1,0 mm.

Resistencia a la abrasión

> 150.000 ciclos martindale, ISO 5470-2

Resistencia a la luz

≥ 6, ISO 105 B02

Solidez al frote

Seco 4/5, húmedo 4/5, ISO 105 X12

Resistencia al fuego

1IM-UNI 9175; EN 1021 part 1/2; BS 5852 part 1; NFPA 260; California TB 117:2013; IMO MED-FTP Code 307 part 8.

Observaciones

Son admisibles ligeras variaciones de color entre diferentes partidas.



Price category

Z

Composition

68% pvc - 2% polyurethane - 30% cotton

Width

± 140 cm / 55 in.

Weight

± 640 gr/m²

Thickness

± 1,0 mm.

Abrasion resistance

> 150.000 rubs, ISO 5470-2

Colour fastness to light

≥ 6, ISO 105 B02

Fastness to rubbing

Dry 4/5, wet 4/5, ISO 105 X12

Fire resistance

1IM-UNI 9175; EN 1021 part 1/2; BS 5852 part 1; NFPA 260; California TB 117:2013; IMO MED-FTP Code 307 part 8.

Remarks

Slight colour differences between different batches are allowed.



fireproof



imo-med



medical

Carina

polipiel / eco leather

Grupo de precio

B

Composición

83% pvc - 11% poliéster - 6% algodón

Ancho

± 140 cm / 55 in.

Peso

± 760 gr/m²

Espesor

± 1,30 mm.

Resistencia a la abrasión

> 25.000 ciclos martindale, ISO 5470-2

Resistencia a la luz

4/5, ISO 105 B02

Solidez al frote

Seco 4/5, húmedo 4/5, ISO 105 X12

Resistencia al fuego

1IM-UNI 9175; EN 1021 part 1/2; BS 5852 part 1; BS 5852 crib5; solo previa solicitud, min. 300 m.; California TB 117:2013; IMO MED-FTP Code 307 part 8.

Observaciones

Son admisibles ligeras variaciones de color entre diferentes partidas.



Price category

B

Composition

83% pvc - 11% polyester - 6% cotton

Width

± 140 cm / 55 in.

Weight

± 760 gr/m²

Thickness

± 1,30 mm.

Abrasion resistance

> 25.000 rubs, ISO 5470-2

Colour fastness to light

4/5, ISO 105 B02

Fastness to rubbing

Dry 4/5, wet 4/5, ISO 105 X12

Fire resistance

1IM-UNI 9175; EN 1021 part 1/2; BS 5852 part 1; BS 5852 crib5; only on request, min. 300 m.; California TB 117:2013; IMO MED-FTP Code 307 part 8.

Remarks

Slight colour differences between different batches are allowed.



fireproof



imo-med